

Steel grades

Electrolytically galvanised flat products



Mild steels - electrolytically zinc coated cold rolled steel flat products for cold forming according to DIN EN 10152

| Designation | | | Mechanical properties (transverse direction) | | | | | Chemical composition | | | | |
|-------------|--------------|---|--|----------------------------|--------------------|----------------------|---------------------------|------------------------------|-------|-------|------|-----|
| Steel name | Steel number | Symbols for the types of available coatings | Yield strength | Tensile strength | Elongation | Plastic strain ratio | Strain hardening exponent | cast analysis % by mass max. | | | | |
| | | | R_e N/mm ² | R_m N/mm ² | A_{80} % min. | r_{90} min. | n_{90} min. | C | P | S | Mn | Ti |
| DC01 | 1.0330 | +ZE | -/280 | 270 - 410 | 28 | - | - | 0,12 | 0,045 | 0,045 | 0,60 | - |
| DC03 | 1.0347 | +ZE | -/240 | 270 - 370 | 34 | 1,3 | - | 0,10 | 0,035 | 0,035 | 0,45 | - |
| DC04 | 1.0338 | +ZE | -/220 | 270 - 350 | 37 | 1,6 | 0,170 | 0,08 | 0,030 | 0,030 | 0,40 | - |
| DC05 | 1.0312 | +ZE | -/200 | 270 - 330 | 39 | 1,9 | 0,190 | 0,06 | 0,025 | 0,025 | 0,35 | - |
| DC06 | 1.0873 | +ZE | -/180 | 270 - 350 | 41 | 2,1 | 0,210 | 0,02 | 0,020 | 0,020 | 0,25 | 0,3 |
| DC07 | 1.0898 | +ZE | -/160 | 250 - 310 | 43 | 2,5 | 0,220 | 0,01 | 0,020 | 0,020 | 0,20 | 0,2 |

Micro-alloyed steels - cold rolled steel flat products with high yield strength for cold forming according to DIN EN 10268; with an additional coating designation, this standard also applies to electrolytically galvanised flat products

| Designation | | Mechanical properties (longitudinal) | | | | | | | Chemical composition | | | | | | | |
|-------------|--------------|--------------------------------------|--------------------------------------|----------------------------|-----------------------|----------------------|----------------------|---------------------------|------------------------------|-----|-----|-------|-------|--------------------|------|------|
| Steel name | Steel number | Proof strength | Bake-Hardening Index | Tensile strength | Elongation | Plastic strain ratio | Plastic strain ratio | Strain hardening exponent | cast analysis % by mass max. | | | | | | | |
| | | $R_{p0,2}$ N/mm ² | BH ₂ N/mm ² | R_m N/mm ² | A_{80} in % min. | r max. | r min. | n min. | C | Si | Mn | P | S | Al _{min.} | Ti | Nb |
| HC180Y | 1.0922 | 180 - 230 | - | 330 - 400 | 35 | - | 1,7 | 0,19 | 0,01 | 0,3 | 0,7 | 0,06 | 0,025 | 0,01 | 0,12 | 0,09 |
| HC180B | 1.0395 | 180 - 230 | 35 | 290 - 360 | 34 | - | 1,6 | 0,17 | 0,06 | 0,5 | 0,7 | 0,06 | 0,030 | 0,015 | - | - |
| HC220Y | 1.0925 | 220 - 270 | - | 340 - 420 | 33 | - | 1,6 | 0,18 | 0,01 | 0,3 | 0,9 | 0,08 | 0,025 | 0,01 | 0,12 | 0,09 |
| HC220I | 1.0346 | 220 - 270 | - | 300 - 380 | 34 | 1,4 | - | 0,18 | 0,07 | 0,5 | 0,6 | 0,05 | 0,025 | 0,015 | 0,05 | - |
| HC220B | 1.0396 | 220 - 270 | 35 | 320 - 400 | 32 | - | 1,5 | 0,16 | 0,08 | 0,5 | 0,7 | 0,085 | 0,030 | 0,015 | - | - |
| HC260Y | 1.0928 | 260 - 320 | - | 380 - 440 | 31 | - | 1,4 | 0,17 | 0,01 | 0,3 | 1,6 | 0,10 | 0,025 | 0,01 | 0,12 | 0,09 |
| HC260I | 1.0349 | 260 - 310 | - | 320 - 400 | 32 | 1,4 | - | 0,17 | 0,07 | 0,5 | 1,2 | 0,05 | 0,025 | 0,015 | 0,05 | - |
| HC260B | 1.0400 | 260 - 320 | 35 | 360 - 440 | 29 | - | - | - | 0,10 | 0,5 | 1,0 | 0,10 | 0,030 | 0,015 | - | - |
| HC260LA | 1.0480 | 260 - 330 | - | 350 - 430 | 26 | - | - | - | 0,10 | 0,5 | 1,0 | 0,030 | 0,025 | 0,015 | 0,15 | 0,09 |
| HC300I | 1.0447 | 300 - 350 | - | 340 - 440 | 30 | 1,4 | - | 0,16 | 0,08 | 0,5 | 0,7 | 0,08 | 0,025 | 0,015 | 0,05 | - |
| HC300B | 1.0444 | 300 - 360 | 35 | 390 - 480 | 26 | - | - | - | 0,10 | 0,5 | 1,0 | 0,12 | 0,030 | 0,015 | - | - |
| HC300LA | 1.0489 | 300 - 380 | - | 380 - 480 | 23 | - | - | - | 0,12 | 0,5 | 1,4 | 0,030 | 0,025 | 0,015 | 0,15 | 0,09 |
| HC340LA | 1.0548 | 340 - 420 | - | 410 - 510 | 21 | - | - | - | 0,12 | 0,5 | 1,5 | 0,030 | 0,025 | 0,015 | 0,15 | 0,09 |
| HC380LA | 1.0550 | 380 - 480 | - | 440 - 580 | 19 | - | - | - | 0,12 | 0,5 | 1,6 | 0,030 | 0,025 | 0,015 | 0,15 | 0,09 |
| HC420LA | 1.0556 | 420 - 520 | - | 470 - 600 | 17 | - | - | - | 0,14 | 0,5 | 1,6 | 0,030 | 0,025 | 0,015 | 0,15 | 0,09 |
| HC460LA | 1.0574 | 460 - 580 | - | 510 - 660 | 13 | - | - | - | 0,14 | 0,6 | 1,8 | 0,030 | 0,025 | 0,015 | 0,15 | 0,09 |
| HC500LA | 1.0573 | 500 - 620 | - | 550 - 710 | 12 | - | - | - | 0,14 | 0,6 | 1,8 | 0,030 | 0,025 | 0,015 | 0,15 | 0,09 |

STEEL SERVICE

COIL TRADE

DIGITAL MARKETPLACE

PROCESSING

CONTRACT PARTNERS

Steel grades

Electrolytically galvanised flat products



Multiphase steel - cold rolled products of multiphase steels for cold forming according to DIN EN 10338; with an additional coating designation, this standard also applies to electrolytically galvanised flat products

| Designation | | Mechanical properties (longitudinal) | | | | | Chemical composition | | | | | | | | | |
|----------------------------|--------------|--------------------------------------|------------------------------------|--------------------|---------------------------------|-------------------------------------|---------------------------------|------|------|-------|-------|---------------------|-------|-------|------|-------|
| Steel name | Steel number | Yield strength | Tensile strength | Elon- gation | Strain hardening exponent | Bake- Hardening Index | cast analysis % by mass max. | | | | | | | | | |
| | | $R_{p0,2}$ N/mm ² | R_m N/mm ² min. | A_{80} % min. | n_{10-UE} min. | BH_2 N/mm ² min. | C | Si | Mn | P | S | Al _{total} | Cr+Mo | Nb+Ti | V | B |
| Dual-phase steel | | | | | | | | | | | | | | | | |
| HCT490X | 1.0939 | 290 - 380 | 490 | 24 | 0,15 | 30 | 0,14 | 0,75 | 2,00 | 0,080 | 0,015 | 0,015 - 1,0 | 1,00 | 0,15 | 0,20 | 0,005 |
| HCT590X | 1.0941 | 330 - 430 | 590 | 20 | 0,14 | 30 | 0,15 | 0,75 | 2,50 | 0,040 | 0,015 | 0,015 - 1,5 | 1,40 | 0,15 | 0,20 | 0,005 |
| HCT780X | 1.0943 | 440 - 550 | 780 | 14 | - | 30 | 0,18 | 0,80 | 2,50 | 0,080 | 0,015 | 0,015 - 2,0 | 1,40 | 0,15 | 0,20 | 0,005 |
| HCT980X | 1.0944 | 590 - 740 | 980 | 10 | - | 30 | 0,20 | 1,00 | 2,90 | 0,080 | 0,015 | 0,015 - 2,0 | 1,40 | 0,15 | 0,20 | 0,005 |
| HCT980XG | 1.0997 | 700 - 800 | 980 | 8 | - | 30 | 0,23 | 1,00 | 2,90 | 0,080 | 0,015 | 0,015 - 2,0 | 1,40 | 0,15 | 0,20 | 0,005 |
| TRIP-steel | | | | | | | | | | | | | | | | |
| HCT690T | 1.0947 | 400 - 520 | 690 | 23 | 0,19 | 40 | 0,24 | 2,00 | 2,20 | 0,080 | 0,015 | 0,015 - 2,0 | 0,60 | 0,20 | 0,20 | 0,005 |
| HCT780T | 1.0948 | 450 - 570 | 780 | 21 | 0,18 | 40 | 0,25 | 2,20 | 2,50 | 0,080 | 0,015 | 0,015 - 2,0 | 0,60 | 0,20 | 0,20 | 0,005 |
| Complex-phase steel | | | | | | | | | | | | | | | | |
| HCT600C | 1.0953 | 350 - 500 | 600 | 16 | - | 30 | 0,18 | 0,80 | 2,20 | 0,080 | 0,015 | 0,015 - 2,0 | 1,00 | 0,15 | 0,20 | 0,005 |
| HCT780C | 1.0954 | 570 - 720 | 780 | 10 | - | 30 | 0,18 | 1,00 | 2,50 | 0,080 | 0,015 | 0,015 - 2,0 | 1,00 | 0,15 | 0,20 | 0,005 |
| HCT980C | 1.0955 | 780 - 950 | 980 | 6 | - | 30 | 0,23 | 1,00 | 2,70 | 0,080 | 0,015 | 0,015 - 2,0 | 1,00 | 0,15 | 0,22 | 0,005 |
| Multiphase steel | | | | | | | | | | | | | | | | |
| HCT1180G2 | 1.0969 | 900 - 1150 | 1180 | 4 | - | 30 | 0,23 | 1,20 | 2,90 | 0,080 | 0,015 | 0,015 - 1,4 | 1,20 | 0,15 | 0,20 | 0,005 |

Coatings according to DIN EN 10152

| Coating designation | Coating thickness per surface | | Minimum value of coating thickness per surface | | Density g/cm ³ |
|---------------------|-------------------------------|-----------------------|--|-----------------------|------------------------------|
| | Thickness μm | Mass g/m ² | Thickness μm | Mass g/m ² | |
| ZE 25/25 | 2,5 | 18 | 1,7 | 12 | 7,1 |
| ZE 50/50 | 5,0 | 36 | 4,1 | 29 | |
| ZE 75/75 | 7,5 | 54 | 6,6 | 47 | |
| ZE 100/100 | 10,0 | 72 | 9,1 | 65 | |